

R930

TYPICAL MATERIAL PROPERTIES

Test	Orientation	Units	Value	Method
Basis Weight		g/m ²	58	ASTM D3776
Composition	Polypropylene	%	30	AATCC 20
	Woodpulp	%	70	
Thickness		mils	11.8	ASTM D1777
		mm	0.30	
Dry Tensile	MD	lbf	11.3	ASTM D5034
	CD	lbf	9	
Wet Tensile	MD	lbf	9.0	
	CD	lbf	7.8	
Speed of Absorbability		1	Seconds	ASTM D5034
Absorbant Capacity		394.3	%	